

# PROTECTAPEEL

PAINT • PROTECT • PEEL

## PROTECTAPEEL

## Vehiclestrip

**Protectapeel Vehiclestrip** is a tough, weather and UV resistant peelable protective coating suitable for use on metals, GRP and stoved paints for up to 12 months. Vehiclestrip protects against staining, paint spillage, graffiti, scratches, paint overspray and can be colour matched to provide an instant colour change or camouflage on vehicles. It can also be used as an alternative method of protection on rolling stock and aggregate carrying vehicles to avoid costly and environmentally harmful chemical clean downs.

**Colour** - Clear. Also available in different colours upon request.

**Health & Safety** - The compound is non toxic and non flammable in the wet state. The dry film waste may be disposed of as low hazard. Please see separate Health & Safety Sheet.

**Application** - **By Lambswool Roller** – Apply 2 coats, allowing 1st to tack off. Apply generously to achieve a **min wet film thickness (WFT) of 250 Microns (100 Microns DFT)**

**By Spray** –Apply with airless spray gun, using a 17 thou tip size and a box coat to achieve a **min wet film thickness (WFT) of 250 Microns (100 Microns DFT)**. To avoid “feather edges”, apply masking tape before the product is applied. Paint up to and over the masking tape edge then remove tape when product is still wet to leave a defined edge.

**A minimum wet film thickness of 250 microns (100 micron dry film thickness) must be achieved, anything less may result in the product becoming difficult to remove.** Do not apply in wet or freezing conditions and protect from rainfall.

The contents of the containers should be mixed thoroughly before use.

**Repair** - If the protective coating rips, repair by lifting the ripped patch and apply a fresh coat to the underside and reseal. Alternatively, cut away the damaged area and apply a fresh coat.

**Drying Time** - A WFT of 250 microns will be tack free in approximately 30 mins at room temperature. Force drying may be used by increasing the surface temperature to a maximum of 50°C and using moving air.

**Surfaces** - Metals, GRP & Stoved Paints.



**Coverage** - One kilo/litre will cover approximately 5m<sup>2</sup> at a WFT of 250 microns.

**Removal** - The dry film can be easily removed either by hand peeling or by pressure hose. Do not remove in freezing conditions as the coating may be brittle.

**External Weather Resistance** - Vehiclestrip is suitable for **up to 12 months exposure**.

**Storage** - Shelf life 12 months. Store at temperatures between 5°C - 25°C. DO NOT ALLOW LIQUID TO FREEZE.

**Clean Down** - Clean rollers and equipment with water immediately after use.

**General Note:** It is important that this product is thoroughly evaluated under production conditions before being commercially adopted (Such an evaluation should incorporate a reference to ageing). The above recommendations are made in good faith for the guidance of users and are without liability. Any queries should be referred to our Technical Sales Department.