

# PROTECTAPEEL

PAINT • PROTECT • PEEL

## PROTECTAPEEL

## Boothstrip

**Protectapeel Boothstrip** is a white, peelable protective coating designed to protect walls, floors and working surfaces within a spray booth from overspray and contamination. The coating will withstand temperatures up to 80°C. The white protective coating provides a light reflective surface for better working conditions and can be over-coated several times and then stripped back as part of the spray booth maintenance programme.

**Colour** - White, Also available in clear for glass windows.

**Health & Safety** - The compound is non toxic and non flammable in the wet state. The dry film waste may be disposed of as low hazard. Please see separate Health & Safety Sheet.

**Application** - **By Lambswool Roller** – Apply 2 coats, allowing 1st to tack off. Apply generously to achieve a **min wet film thickness (WFT) of 250 Microns (75 Microns DFT)**

**By Spray** – Apply with airless spray gun, using a 17 thou tip size and a box coat to achieve a **min wet film thickness (WFT) of 250 Microns (75 Microns DFT)**. To avoid “feather edges”, apply masking tape before the product is applied. Paint up to and over the masking tape edge then remove tape when product is still wet to leave a defined edge.

**A minimum wet film thickness of 250 microns (75 micron dry film thickness) must be achieved, anything less may result in the product becoming difficult to remove.** Do not apply in wet or freezing conditions and protect from rainfall.

The contents of the containers should be mixed thoroughly before use.

**Heat Resistance (For use in spray booth ovens)** - The dried film will remain peelable after at least 400 hours at no more than 80°C with no overcoat. It is the responsibility of the end user to determine the effective lifetime of the material under the conditions of actual use. This is best achieved by peeling a small area at regular intervals.

**Repair** - If the protective coating rips, repair by lifting the ripped patch and apply a fresh coat to the underside and reseal. Alternatively, cut away the damaged area and apply a fresh coat.

**Drying Time** - A WFT of 250 microns will be tack free in approximately 45 mins at room temperature. Force drying may be used by increasing the surface temperature to a maximum of 50°C and using moving air.



**Surfaces** - Plastic and Painted Surfaces.

**Coverage** - One kilo/litre will cover approximately 4m<sup>2</sup> at a WFT of 250 microns.

**Removal** - The dry film can be easily removed either by hand peeling or by pressure hose. Do not remove in freezing conditions as the coating may be brittle.

**External Weather Resistance** - Boothstrip is suitable for **INTERNAL USE ONLY**.

**Storage** - Shelf life 12 months. Store at temperatures between 5°C - 25°C. **DO NOT ALLOW LIQUID TO FREEZE.**

**Clean Down** - Clean rollers and equipment with water immediately after use.

**General Note:** It is important that this product is thoroughly evaluated under production conditions before being commercially adopted (Such an evaluation should incorporate a reference to ageing). The above recommendations are made in good faith for the guidance of users and are without liability. Any queries should be referred to our Technical Sales Department.